

Technical Data Sheet

TALBROS TNA 32N NON ASBESTOS GASKET JOINTING SHEET

Applications:

High performance gasket material with high temperature resistance, oil resistance & high resilience. Neoprene Binder, water, gases, fuels and versatile media resistance properties. Excellent thermal, chemical & mechanical properties.

General data:

Material Composition (Type of fibres)

Aramid Fiber, Mineral Fibre.

Binders

Neoprene Elastomers

OPERATING CONDITION

Max. Peak Temp

400°C

Max. Continuous Temp

270°C

Max. Continuous Temp. With steam

240°C

Max. Operating Pressure

150 Kg/cm²

Physical Properties:

The following information applies to material thickness 2.0 mm.

S. No	PROPERTIES	TEST METHOD	UNIT	SPECIFIED VALUE
1.	Density		gm/cm ³	1.70~2.00
2.	Tensile Strength			
	ACC to ASTM F152(ACROSS GRAIN)		N/mm ²	> 10.5
	ACC to DIN52910 (ACROSS GRAIN)		N/mm ²	> 8
3.	Compressibility	ASTM F36A	%	5 – 15
4.	Recovery	ASTM F36A	%	> 50
5.	Fluid Absorption	ASTM F 146		
	(a) In ASTM OIL No. 3			
	Increase in Mass		%	< 10
	Increase in Thickness		%	< 10
	(b) In Fuel B	ASTM F 146		
	Increase in Mass		%	< 10
	Increase in Thickness		%	< 10
	(c) In Water/Antifreeze	ASTM F 146		
	Increase in Mass		%	< 10
	Increase in Thickness		%	< 7
6.	Ignition Loss	DIN 52911	%	< 30
7.	Sealability Against Nitrogen	DIN 3535	cm ³ /min	< 1.0
8.	Stress Resistance			
	16h 300° C	DIN 52913	N/mm ²	~20
	16h 175° C	DIN 52913	N/mm ²	~30

Standard Sheet Size		1500x2000 mm, 1500x4000mm, 1500x1500mm 1500x4500 mm, 1500x3000mm, 2000x3000 mm
Thickness		0.25 mm to 6.00 mm (For Non-Metallic Range) 0.80 mm to 6.00 mm (For Metallic Range)
Tolerance	Thickness	< 1mm = ± 0.10 mm > 1mm = $\pm 10\%$
	Length	± 50 mm
	Width	± 50 mm

All data quoted above are based on years of experience in production & operation of sealing elements, in view of the wide variety of possible installation & operating conditions one cannot draw final conclusion in all application cases regarding the behavior in gasket joint. The data may not therefore, be used to support any warranty claims should you have any doubts about the choice of gasket material, please refer to us. Our engineering cell will be happy to assist you.

Talbros Sealing Materials P Ltd
Plot No. 60, Sec-6, Faridabad Haryana 121006 (India)
Phone No. +91-129-4067000 www.bnt-talbros.com